

BOND TEST GUIDE

The purpose of the Bond Test is to assure that the preparation is adequate for the primer to bond to the substrate.

Prior to application of all CRYL-A-FLEX systems, it is recommended that a bond test be conducted. The bond of the CRYL-A-PRIME P-101 to the substrate shall be greater than the tensile strength of the substrate. A successful test shows substrate material and sheared aggregate adhering fully to the sample. If only laitance or a small amount of the substrate is attached, further preparation is required.

This is a very simple procedure that uses the CRYL-A-PRIME P-101, with or without the CRYL-A-BOND, Q-11 sand, CRYL-A-CURE (BPO) and a hammer and chisel.

The procedure is as follows:

Pour 6-8 ounces (170-225 ml) of CRYL-A-PRIME P-101 into a paper/plastic cup. Add 1-2 tablespoons (10-20 ml) of CRYL-A-CURE (BPO) and mix with a paint stick for 15-30 seconds. Add Q-11 size sand (1.5 times the volume of resin) and mix well to achieve a very WET slurry. **NOTE:** if this mix is too dry it will not leave enough resin to soak into the substrate. A good indication of a wet mix is that there should be excessive resin on the surface in the cup.

Place 3-4 inch (75-100 mm) diameter 1/4 – 1/2 inch (6.4-12.8 mm) thick patties on the substrate.

Allow to cure 1 hour 68 F (20 C). Verify that the patties are tack-free and cooled to the substrate temperature.

Remove with a hammer and chisel. Examine the bottom of the patty. There should be 1/8 - 1/2 inch (3-13 mm) of concrete and fractured aggregate attached.

If the bottom of the patty is tacky, has only laitance or fines attached, then further surface preparation is necessary.

CAUTION

CRYL-A-FLEX resins are flammable liquids in their uncured state. Smoking, open flames or sparks should not be permitted during the handling of the product. Workers should wear protective clothing consisting of splash proof goggles, impermeable gloves and, where exposure limits are exceeded, an organic vapor respirator should be used. Adequate cross ventilation should be provided and explosion proof fans may be required. All foodstuffs must be removed during application of the system. **Follow the Hazardous Materials Identification System labeling guide for proper personal protective equipment to use when handling this product. Use only as directed. KEEP OUT OF REACH OF CHILDREN. If substrate and/or material temperature is above 90 F (32 C), Do Not apply material. Detailed application instructions should be obtained, read and understood prior to commencement of application.**

Before using any DUR-A-FLEX, Inc. product, be sure the Material Safety Data Sheet is read and understood.