

CRYL-A-GARD SL

DESCRIPTION

CRYL-A-GARD SL is a 100% reactive, fast curing, high strength, methyl methacrylate (MMA) based acrylic flooring system. It is a 1/8 - 1/4 inch (3-6 mm) self-leveling overlay system composed of a prime coat, a self-leveling body coat and a topcoat. The finished surface is typically smooth. This system cannot be thinned with solvents.

BENEFITS

- VOC compliant, <100 g/L
- Fast cure, full strength in less than one hour
- NSF Registered
- Indoor and outdoor applications
- UV resistant
- Resistant to chemical attack
- Seamless, no cold joints, always bonds to itself
- Meets USDA/FDA and CFIA requirements
- Use over a wide temperature range, even below freezing
- Available with Bio-Pruf® antibacterial and fungal additive

TYPICAL USES

- Laboratories
- Traffic Aisles
- Heavy Industry
- Walk In Coolers
- Loading Docks
- Manufacturing Areas
- Food Processing Areas
- Bottling Areas
- Freezers
- Grocery Stores

COLORS

CRYL-A-GARD SL is available in standard colors. Please refer to the CRYL-A-FLEX Color Chart.

SURFACE PREPARATION

The substrate must be dry and free of oil, grease, dirt, bituminous and other contaminants. Unsound concrete and laitance should be removed by appropriate mechanical means.

PACKAGING & STORAGE CONDITIONS

CRYL-A-GARD SL resins are available in 5-gallon (19 liter) pails, and 50-gallon (190 liter) drums. CRYL-A-CURE is available in 1 gallon (3.8 liter) cans, 5-gallon (19 liter) pails, and 55-pound (25 kg) boxes. SL Filler Blend is available in 40-pound (18.1 kg) bags.

Store in a cool and dry place below 85 F (30 C), out of direct sunlight. Do not store near open flame or food. The shelf life is 6 months from ship date in the original unopened containers.

APPLICATION METHOD / SPREAD RATE

CRYL-A-PRIME should be applied by brush or roller at 80-125 Sq Ft per gallon. (2-3m² per liter) Substrates that are very porous may require an additional primer application. Body coat is composed of 7 quarts (6.7 liter) of CRYL-A-GLAZE resin, one 40 lb bag (18.1 kg) SL Filler Blend, pigment and CRYL-A-CURE. This mix will yield 38 Sq Ft at 1/8 inch (3.5 m² at 3mm) thick. Trowel or gage rake to the appropriate thickness, then use a spiked roller to release any trapped air. The cured system is topcoated with clear CRYL-A-TOP. The appropriate amount of CRYL-A-CURE is determined by using the CRYL-A-FLEX Mixing Chart.

GUIDE SPECIFICATIONS

This product is part of the DUR-A-FLEX family of polymer systems. Please contact DUR-A-FLEX for complete three part guide specs.

DRAWINGS AND DETAILS

Standard CAD drawings and details are available for coves, drains, breaches, transitions, etc. Please contact DUR-A-FLEX for actual drawings.

JOINT GUIDELINES

Refer to the Joint Guidelines for complete details on our website

MOISTURE CONCERNS

Please refer to the Floor Evaluation Guidelines in the Contractor's Center of our website for a step-by-step process to determine the condition of the concrete.

CHEMICAL RESISTANCE

This product is resistant to many common chemicals. Refer to the Chemical Resistance Chart on our website or consult with our technical staff for non-listed materials.

CLEANING

This product is considered to be a low maintenance flooring solution, however, certain textures and service environments require specific procedures. Please refer to the master Cleaning Guide on our website.

BOND TEST

Prior to full application of the primer, bond tests shall be conducted to determine adequacy of substrate preparation and bond. The bond of the primer to the substrate should be greater than the tensile strength of the substrate. A successful test shows substrate material and sheared aggregate adhering fully to the sample.

CURE

CRYL-A-GARD SL system will cure in 45-60 minutes. At this time, the floor is fully functional.

TECHNICAL INFORMATION

CRYL-A-GARD SL is part of a family of special repair and wearing materials supplied by DUR-A-FLEX. If you require further information on this or any of our other products, please contact our Technical Department.

PHYSICAL CHARACTERISTICS

Percent Reactive	100%
VOC	<100 g/L
Pot Life @ 68 F (20 C)	10-20 minutes
Cure Rate @ 68 F (20 C)	30-60 minutes
Recoat Time	60 minutes
Tensile Strength	2,175 psi (15 N/mm ²)
Compressive Strength (Filled System)	6,000-8,000 psi (41-56 N/mm ²)

CAUTION

Adequate cross ventilation should be provided. Read, understand and follow Safety Data Sheets and Application Instructions of this flooring system prior to use. Follow the Hazardous Materials Identification System labeling guide for proper personal protective equipment to use when handling this product. Use only as directed. **If substrate and/or material temperature is above 90 F (32 C), Do Not apply material.**

Before using any DUR-A-FLEX, Inc. product, be sure the Safety Data Sheet is read and understood.